

Stranded Bare Copper

CONSTRUCTION AT A GLANCE

CONDUCTOR TYPE **1**
COPPER

APPLICATIONS

- Suitable for use in substations as uninsulated hook ups, jumpers, and grounds

CONSTRUCTION DETAILS

- Bare copper conductor
- Available in soft-drawn (annealed), medium-hard-drawn, or hard-drawn tempers
- Concentric-lay or combination unilay stranded, depending on stranding and temper


SPECIFICATIONS

Southwire's Bare Copper Conductor meets or exceeds applicable ASTM specifications:

- **B 1:** Hard-Drawn Copper Wire
- **B 2:** Medium-Hard-Drawn Copper Wire
- **B 3:** Soft or Annealed Copper Wire
- **B 8:** Concentric-Lay-Stranded Copper Conductor, Hard, Medium-Hard or Soft
- **B 787:** 19 Wire Combination Unilay-Stranded Copper Conductor

OPTIONS

- Solid (1 strand)
- Stranded (7, 19, 37, 61 strands)



| Size (AWG or kcmil) | Stranding | Stranding Class | Weight (lbs/1000 ft) | Diameter (inches) | | Hard Drawn | | Medium-Hard Drawn | | Soft Drawn (Annealed) | | Allowable Ampacity+ |
|---------------------|-----------|-----------------|----------------------|-------------------|----------------|----------------------|------------------------------------|----------------------|------------------------------------|-----------------------|------------------------------------|---------------------|
| | | | | Individual | Complete Cable | Rated Strength (lbs) | R _{dc} @ 20°C (Ω/1000 ft) | Rated Strength (lbs) | R _{dc} @ 20°C (Ω/1000 ft) | Rated Strength (lbs) | R _{dc} @ 20°C (Ω/1000 ft) | |
| 8 | 7 | B | 51 | 0.049 | 0.146 | 777 | 0.6663 | 610 | 0.6629 | 499 | 0.6408 | 95 |
| 6 | 7 | B | 81 | 0.061 | 0.184 | 1228 | 0.4191 | 959 | 0.4169 | 794 | 0.4030 | 130 |
| 4 | 7 | A, B | 129 | 0.077 | 0.232 | 1938 | 0.2636 | 1505 | 0.2622 | 1320 | 0.2534 | 170 |
| 3 | 7 | A, B | 163 | 0.087 | 0.260 | 2433 | 0.2090 | 1885 | 0.2079 | 1670 | 0.2010 | 200 |
| 2 | 7 | A, B | 205 | 0.097 | 0.292 | 3050 | 0.1660 | 2360 | 0.1650 | 2110 | 0.1578 | 230 |
| 1 | 7 | A | 258 | 0.109 | 0.328 | 3801 | 0.1316 | 2955 | 0.1309 | 2552 | 0.1252 | 265 |
| 1/0 | 7 | A, AA | 326 | 0.123 | 0.368 | 4752 | 0.1042 | 3705 | 0.1037 | 3221 | 0.1002 | 310 |
| 1/0 | 19 | B | 326 | 0.075 | 0.373 | 4752 | 0.1042 | 3705 | 0.1037 | 3221 | 0.1002 | 310 |
| 2/0 | 7 | A, AA | 411 | 0.138 | 0.414 | 5926 | 0.0827 | 4640 | 0.0822 | 4062 | 0.0795 | 355 |
| 2/0 | 19 | B | 411 | 0.084 | 0.418 | 6690 | 0.0827 | 4765 | 0.0822 | 4024 | 0.0795 | 355 |
| 3/0 | 7 | A, AA | 518 | 0.155 | 0.464 | 7366 | 0.0656 | 5812 | 0.0652 | 5118 | 0.0630 | 410 |
| 4/0 | 7 | A, AA | 653 | 0.174 | 0.522 | 9154 | 0.0520 | 7278 | 0.0517 | 6459 | 0.0500 | 480 |
| 4/0 | 19 | B | 653 | 0.106 | 0.528 | 9617 | 0.0520 | 7479 | 0.0517 | 6453 | 0.0500 | 480 |
| 250 | 19 | A | 772 | 0.115 | 0.574 | 11360 | 0.0440 | 8836 | 0.0438 | 7627 | 0.0423 | 530 |
| 250 | 37 | B | 772 | 0.082 | 0.575 | 11600 | 0.0440 | 8952 | 0.0438 | 7940 | 0.0423 | 530 |
| 300 | 19 | A | 926 | 0.126 | 0.628 | 13510 | 0.0367 | 10530 | 0.0365 | 9160 | 0.0353 | 590 |
| 350 | 19 | A | 1081 | 0.136 | 0.679 | 15590 | 0.0314 | 12200 | 0.0313 | 10680 | 0.0302 | 650 |
| 500 | 37 | A, B | 1544 | 0.116 | 0.814 | 22510 | 0.0220 | 17550 | 0.0219 | 15240 | 0.0212 | 810 |
| 600 | 37 | A, AA | 1853 | 0.127 | 0.891 | 27020 | 0.0183 | 21060 | 0.0183 | 18300 | 0.0176 | 910 |
| 750 | 61 | A, B | 2316 | 0.111 | 0.998 | 34090 | 0.0147 | 26510 | 0.0146 | 22890 | 0.0141 | 1040 |
| 1000 | 61 | A, B | 3088 | 0.128 | 1.152 | 45030 | 0.0110 | 35100 | 0.0109 | 30500 | 0.0106 | 1240 |

+ Ampacity based on 75°C conductor temperature; 25°C ambient temperature; 2 ft./sec. wind in sun.

* Numbers shown above are for concentrically stranded constructions and may vary slightly for combination unilay stranded constructions. Dimensions and weights shown above are nominal and subject to industry tolerances.



Stranded Bare Copper

CONSTRUCTION AT A GLANCE

CONDUCTOR TYPE **1**
COPPER

APPLICATIONS

- Suitable for use in substations as uninsulated hook ups, jumpers, and grounds

CONSTRUCTION DETAILS

- Bare copper conductor
- Available in soft-drawn (annealed), medium-hard-drawn, or hard-drawn tempers
- Concentric-lay or combination unilay stranded, depending on stranding and temper

SPECIFICATIONS

Southwire's Bare Copper Conductor meets or exceeds applicable ASTM specifications:

- **B 1:** Hard-Drawn Copper Wire
- **B 2:** Medium-Hard-Drawn Copper Wire
- **B 3:** Soft or Annealed Copper Wire
- **B 8:** Concentric-Lay-Stranded Copper Conductor, Hard, Medium-Hard or Soft
- **B 787:** 19 Wire Combination Unilay-Stranded Copper Conductor

OPTIONS

- Solid (1 strand)
- Stranded (7, 19, 37, 61 strands)



| Size (AWG or kcmil) | Stranding | Stranding Class | Weight (lbs/1000 ft) | Diameter (inches) | | Hard Drawn | | Medium-Hard Drawn | | Soft Drawn (Annealed) | | Allowable Ampacity+ |
|---------------------|-----------|-----------------|----------------------|-------------------|----------------|----------------------|------------------------------------|----------------------|------------------------------------|-----------------------|------------------------------------|---------------------|
| | | | | Individual | Complete Cable | Rated Strength (lbs) | R _{dc} @ 20°C (Ω/1000 ft) | Rated Strength (lbs) | R _{dc} @ 20°C (Ω/1000 ft) | Rated Strength (lbs) | R _{dc} @ 20°C (Ω/1000 ft) | |
| 8 | 7 | B | 51 | 0.049 | 0.146 | 777 | 0.6663 | 610 | 0.6629 | 499 | 0.6408 | 95 |
| 6 | 7 | B | 81 | 0.061 | 0.184 | 1228 | 0.4191 | 959 | 0.4169 | 794 | 0.4030 | 130 |
| 4 | 7 | A, B | 129 | 0.077 | 0.232 | 1938 | 0.2636 | 1505 | 0.2622 | 1320 | 0.2534 | 170 |
| 3 | 7 | A, B | 163 | 0.087 | 0.260 | 2433 | 0.2090 | 1885 | 0.2079 | 1670 | 0.2010 | 200 |
| 2 | 7 | A, B | 205 | 0.097 | 0.292 | 3050 | 0.1660 | 2360 | 0.1650 | 2110 | 0.1578 | 230 |
| 1 | 7 | A | 258 | 0.109 | 0.328 | 3801 | 0.1316 | 2955 | 0.1309 | 2552 | 0.1252 | 265 |
| 1/0 | 7 | A, AA | 326 | 0.123 | 0.368 | 4752 | 0.1042 | 3705 | 0.1037 | 3221 | 0.1002 | 310 |
| 1/0 | 19 | B | 326 | 0.075 | 0.373 | 4752 | 0.1042 | 3705 | 0.1037 | 3221 | 0.1002 | 310 |
| 2/0 | 7 | A, AA | 411 | 0.138 | 0.414 | 5926 | 0.0827 | 4640 | 0.0822 | 4062 | 0.0795 | 355 |
| 2/0 | 19 | B | 411 | 0.084 | 0.418 | 6690 | 0.0827 | 4765 | 0.0822 | 4024 | 0.0795 | 355 |
| 3/0 | 7 | A, AA | 518 | 0.155 | 0.464 | 7366 | 0.0656 | 5812 | 0.0652 | 5118 | 0.0630 | 410 |
| 4/0 | 7 | A, AA | 653 | 0.174 | 0.522 | 9154 | 0.0520 | 7278 | 0.0517 | 6459 | 0.0500 | 480 |
| 4/0 | 19 | B | 653 | 0.106 | 0.528 | 9617 | 0.0520 | 7479 | 0.0517 | 6453 | 0.0500 | 480 |
| 250 | 19 | A | 772 | 0.115 | 0.574 | 11360 | 0.0440 | 8836 | 0.0438 | 7627 | 0.0423 | 530 |
| 250 | 37 | B | 772 | 0.082 | 0.575 | 11600 | 0.0440 | 8952 | 0.0438 | 7940 | 0.0423 | 530 |
| 300 | 19 | A | 926 | 0.126 | 0.628 | 13510 | 0.0367 | 10530 | 0.0365 | 9160 | 0.0353 | 590 |
| 350 | 19 | A | 1081 | 0.136 | 0.679 | 15590 | 0.0314 | 12200 | 0.0313 | 10680 | 0.0302 | 650 |
| 500 | 37 | A, B | 1544 | 0.116 | 0.814 | 22510 | 0.0220 | 17550 | 0.0219 | 15240 | 0.0212 | 810 |
| 600 | 37 | A, AA | 1853 | 0.127 | 0.891 | 27020 | 0.0183 | 21060 | 0.0183 | 18300 | 0.0176 | 910 |
| 750 | 61 | A, B | 2316 | 0.111 | 0.998 | 34090 | 0.0147 | 26510 | 0.0146 | 22890 | 0.0141 | 1040 |
| 1000 | 61 | A, B | 3088 | 0.128 | 1.152 | 45030 | 0.0110 | 35100 | 0.0109 | 30500 | 0.0106 | 1240 |

+ Ampacity based on 75°C conductor temperature; 25°C ambient temperature; 2 ft./sec. wind in sun.

* Numbers shown above are for concentrically stranded constructions and may vary slightly for combination unilay stranded constructions. Dimensions and weights shown above are nominal and subject to industry tolerances.

