


# Bare Copper Wire and Cable

Bare Copper Conductor. Solid and Stranded .



## APPLICATIONS

Solid and stranded (classes AA and A) bare copper are suitable for overhead transmission and distribution applications. Stranded conductor of greater flexibility (classes B and C) are suitable for uninsulated hook up, jumpers, and grounds in electrical construction. Soft Drawn copper is unilay construction.

## SPECIFICATIONS

Southwire's bare copper wire and cable meets or exceeds the following ASTM specifications:

- B-1 Hard-Drawn Copper Wire.
- B-2 Medium-Hard Copper Wire.
- B-3 Soft or Annealed Copper Wire.
- B-8 Concentric-Lay-Stranded Hard, Medium-Hard or Soft Copper Conductor.
- B-33 Tinned Conductors
- B-787 19 Wire Combination Unilay-Stranded Soft copper wire.

## CONSTRUCTION

Bare copper, solid or stranded. Available in tempers hard, medium-hard, or soft. Stranded conductors are concentrically stranded in hard and medium-hard tempers and are Combination Unilay stranded in the soft-drawn temper.

# Bare Copper

Size (AWG)	Weight (lbs/1000 ft)	Diameter (mils)	Circular Mil Area (mils)	Hard Drawn		Medium-Hard Drawn		Soft-Drawn (Annealed)		Allowable Ampacity+
				Rated Strength (lbs)	DC Resistance (ohms/1000 ft) @ 20°C	Rated Strength (lbs)	DC Resistance (ohms/1000 ft) @ 20°C	Rated Strength (lbs)	DC Resistance (ohms/1000 ft) @ 20°C	
<b>SOLID</b>										
14	12.4	64.1	4110	213.5	2.626	166.6	2.613	124.2	2.525	--
13	15.7	72	5180	268.0	2.083	208.8	2.072	156.6	2.003	--
12	19.8	80.8	6530	336.9	1.652	261.2	1.643	197.5	1.588	--
11	24.9	90.7	8230	422.9	1.310	327.6	1.303	249.0	1.260	--
10	31.4	101.9	10380	529.2	1.039	410.4	1.033	314.0	.999	--
9	39.6	114.4	13090	661.2	.824	514.2	.820	380.5	.792	--
8	50	128.5	16510	826.0	.653	643.9	.650	479.8	.628	95
7	63	144.3	20820	1030.0	.518	806.6	.515	605.0	.498	105
6	79.4	162	26240	1280.0	.411	1010.0	.409	762.9	.395	125
5	100.2	181.9	33090	1591.0	.326	1265.0	.324	961.9	.313	145
4	126.3	204.3	41740	1970.0	.258	1584.0	.257	1213.0	.249	170
3	159.3	229.4	52620	2439.0	.205	1984.0	.204	1530.0	.197	195
2	200.9	257.6	66360	3003.0	.163	2450.0	.162	1929.0	.156	225
1	253.3	289.3	83690	3688.0	.129	3024.0	.128	2432.0	.124	260


+Ampacity based on 75°C conductor temperature; 25°C ambient temperature; 2 ft./sec. wind in sun.

# Bare Copper

Size (AWG)	Stranding	Stranding Class	Weight (lbs/1000 ft)	Diameter (mils)		Hard Drawn		Medium-Hard Drawn		Soft-Drawn (Annealed)		Allowable Ampacity+
				Individual Wires	Complete Conductor	Rated Strength (lbs)	DC Resistance (ohms/1000 ft) @ 20°C	Rated Strength (lbs)	DC Resistance (ohms/1000 ft) @ 20°C	Rated Strength (lbs)	DC Resistance (ohms/1000 ft) @ 20°C	
<b>STRANDED</b>												
8	7	B	51	49	146	777	.6663	610	.6629	499	.6408	95
6	7	B	81	61	184	1228	.4191	959	.4169	794	.4030	130
4	7	A, B	128.9	77	232	1938	.2636	1505	.2622	1320	.2534	170
3	7	A, B	162.5	87	260	2433	.2090	1885	.2079	1670	.2010	200
2	7	A, B	204.9	97	292	3050	.1660	2360	.1650	2110	.1578	230
1	7	A	258.4	109	328	3801	.1316	2955	.1309	2552	.1252	265
1/0	7	A, AA	326.1	123	368	4752	.1042	3705	.1037	3221	.1002	310
2/0	7	A, AA	410.9	138	414	5926	.08267	4640	.08224	4062	.07949	355
2/0	19	B	410.9	84	418	6690	.08267	4765	.08224	4024	.07949	355
3/0	7	A, AA	518.1	155	464	7366	.06556	5812	.06522	5118	.06304	410
4/0	7	A, AA	653.3	174	522	9154	.05199	7278	.05172	6459	.04999	480
4/0	19	B	653.3	106	528	9617	.05199	7479	.05172	6453	.04999	480
250	19	A	771.9	115	574	11360	.04400	8836	.04378	7627	.04231	530
250	37	B	771.9	82	575	11600	.04400	8952	.04378	7940	.04231	530
300	19	A	926.2	126	628	13510	.03667	10530	.03648	9160	.03526	590
350	19	A	1080.6	136	679	15590	.03143	12200	.03127	10680	.03022	650
500	37	A, B	1543.8	116	814	22510	.02200	17550	.02189	15240	.02116	810
600	37	A, AA	1852.5	127	891	27020	.01834	21060	.01825	18300	.01763	910
750	61	A, B	2315.6	111	998	34090	.01467	26510	.01459	22890	.01410	1040
1000	61	A, B	3087.5	128	1152	45030	.01100	35100	.01094	30500	.01058	1240
+Ampacity based on 75°C conductor temperature; 25°C ambient temperature; 2 ft./sec. wind in sun.												

# Bare Copper Wire and Cable

Bare Copper Conductor. Solid and Stranded .



## APPLICATIONS

Solid and stranded (classes AA and A) bare copper are suitable for overhead transmission and distribution applications. Stranded conductor of greater flexibility (classes B and C) are suitable for uninsulated hook up, jumpers, and grounds in electrical construction. Soft Drawn copper is unilay construction.

## SPECIFICATIONS

Southwire's bare copper wire and cable meets or exceeds the following ASTM specifications:

- B-1 Hard-Drawn Copper Wire.
- B-2 Medium-Hard Copper Wire.
- B-3 Soft or Annealed Copper Wire.
- B-8 Concentric-Lay-Stranded Hard, Medium-Hard or Soft Copper Conductor.
- B-33 Tinned Conductors
- B-787 19 Wire Combination Unilay-Stranded Soft copper wire.

## CONSTRUCTION

Bare copper, solid or stranded. Available in tempers hard, medium-hard, or soft. Stranded conductors are concentrically stranded in hard and medium-hard tempers and are Combination Unilay stranded in the soft-drawn temper.

# Bare Copper

Size (AWG)	Weight (lbs/1000 ft)	Diameter (mils)	Circular Mil Area (mils)	Hard Drawn		Medium-Hard Drawn		Soft-Drawn (Annealed)		Allowable Ampacity+
				Rated Strength (lbs)	DC Resistance (ohms/1000 ft) @ 20°C	Rated Strength (lbs)	DC Resistance (ohms/1000 ft) @ 20°C	Rated Strength (lbs)	DC Resistance (ohms/1000 ft) @ 20°C	
<b>SOLID</b>										
14	12.4	64.1	4110	213.5	2.626	166.6	2.613	124.2	2.525	--
13	15.7	72	5180	268.0	2.083	208.8	2.072	156.6	2.003	--
12	19.8	80.8	6530	336.9	1.652	261.2	1.643	197.5	1.588	--
11	24.9	90.7	8230	422.9	1.310	327.6	1.303	249.0	1.260	--
10	31.4	101.9	10380	529.2	1.039	410.4	1.033	314.0	.999	--
9	39.6	114.4	13090	661.2	.824	514.2	.820	380.5	.792	--
8	50	128.5	16510	826.0	.653	643.9	.650	479.8	.628	95
7	63	144.3	20820	1030.0	.518	806.6	.515	605.0	.498	105
6	79.4	162	26240	1280.0	.411	1010.0	.409	762.9	.395	125
5	100.2	181.9	33090	1591.0	.326	1265.0	.324	961.9	.313	145
4	126.3	204.3	41740	1970.0	.258	1584.0	.257	1213.0	.249	170
3	159.3	229.4	52620	2439.0	.205	1984.0	.204	1530.0	.197	195
2	200.9	257.6	66360	3003.0	.163	2450.0	.162	1929.0	.156	225
1	253.3	289.3	83690	3688.0	.129	3024.0	.128	2432.0	.124	260

+Ampacity based on 75°C conductor temperature; 25°C ambient temperature; 2 ft./sec. wind in sun.

# Bare Copper

Size (AWG)	Stranding	Stranding Class	Weight (lbs/1000 ft)	Diameter (mils)		Hard Drawn		Medium-Hard Drawn		Soft-Drawn (Annealed)		Allowable Ampacity+
				Individual Wires	Complete Conductor	Rated Strength (lbs)	DC Resistance (ohms/1000 ft) @ 20°C	Rated Strength (lbs)	DC Resistance (ohms/1000 ft) @ 20°C	Rated Strength (lbs)	DC Resistance (ohms/1000 ft) @ 20°C	
<b>STRANDED</b>												
8	7	B	51	49	146	777	.6663	610	.6629	499	.6408	95
6	7	B	81	61	184	1228	.4191	959	.4169	794	.4030	130
4	7	A, B	128.9	77	232	1938	.2636	1505	.2622	1320	.2534	170
3	7	A, B	162.5	87	260	2433	.2090	1885	.2079	1670	.2010	200
2	7	A, B	204.9	97	292	3050	.1660	2360	.1650	2110	.1578	230
1	7	A	258.4	109	328	3801	.1316	2955	.1309	2552	.1252	265
1/0	7	A, AA	326.1	123	368	4752	.1042	3705	.1037	3221	.1002	310
2/0	7	A, AA	410.9	138	414	5926	.08267	4640	.08224	4062	.07949	355
2/0	19	B	410.9	84	418	6690	.08267	4765	.08224	4024	.07949	355
3/0	7	A, AA	518.1	155	464	7366	.06556	5812	.06522	5118	.06304	410
4/0	7	A, AA	653.3	174	522	9154	.05199	7278	.05172	6459	.04999	480
4/0	19	B	653.3	106	528	9617	.05199	7479	.05172	6453	.04999	480
250	19	A	771.9	115	574	11360	.04400	8836	.04378	7627	.04231	530
250	37	B	771.9	82	575	11600	.04400	8952	.04378	7940	.04231	530
300	19	A	926.2	126	628	13510	.03667	10530	.03648	9160	.03526	590
350	19	A	1080.6	136	679	15590	.03143	12200	.03127	10680	.03022	650
500	37	A, B	1543.8	116	814	22510	.02200	17550	.02189	15240	.02116	810
600	37	A, AA	1852.5	127	891	27020	.01834	21060	.01825	18300	.01763	910
750	61	A, B	2315.6	111	998	34090	.01467	26510	.01459	22890	.01410	1040
1000	61	A, B	3087.5	128	1152	45030	.01100	35100	.01094	30500	.01058	1240
+Ampacity based on 75°C conductor temperature; 25°C ambient temperature; 2 ft./sec. wind in sun.												